Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1.4.8 Date: 02/02/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	5/1/20	2/2/20	22500	28	277	12.31	12.7
2.	"	"	"	"	"	295	13.11	
3.	"	"	"	"	"	289	12.84	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8 Date: 02/02/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	5/1/20	2/2/20	22500	28	259	11.51	12.50
2.	"	"	"	"	"	288	12.8	
3.	"	"	"	"	"	300	13.33	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8 Date: 02/02/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	5/1/20	2/2/20	22500	28	285	12.66	12.60
2.	"	"	"	"	"	276	12.26	
3.	"	"	"	"	"	290	12.88	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8 Date: 17/02/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	20/1/20	17/2/20	22500	28	269	11.90	9.28
2.	"	"	"	"	"	287	12.75	
3.	"	"	"	"	"	298	13.20	

SHARMA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8 Date: 17/02/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	20/1/20	17/2/20	22500	28	290	12.88	12.97
2.	"	"	"	"	"	305	13.55	
3.	"	"	"	"	"	281	12.48	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8 Date: 28/01/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength-N/mm2	Average
1.	Kavery Layout	20/1/20	28/1/20	22500	7	172	7.64	8.08
2.	"	"	"	"	"	179	7.95	
3.	"	"	"	"	"	195	8.66	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8 Date: 12/01/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	5/1/20	12/1/20	22500	7	179	7.90	7.60
2.	"	"	"	"	"	155	6.80	
3.	"	"	"	"	"	183	8.10	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ SIDES- LAYOUT Date: 24/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength-N/mm2	Average
1.	Sides concrete	27/1/20	24/2/20	22500	28	532	23.65	23.71
2.	Kavery	"	"	"	"	528	23.46	
3.	Layout	"	"	"	"	516	22.93	
4.	"	"	"	"	"	525	23.33	
5.	"	"	"	"	"	546	24.26	
6.	"	"	"	"	"	555	24.66	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ SIDES- LAYOUT Date: 24/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Sides concrete	27/1/20	24/2/20	22500	28	545	24.22	23.91
2.	Kavery	"	"	"	"	536	23.82	
3.	Layout	"	"	"	"	529	23.51	
4.	"	"	"	"	"	530	23.55	
5.	"	"	"	"	"	542	24.08	
6.	"	"	"	"	"	547	24.31	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8

Date: 12/01/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	5/1/20	12/1/20	22500	7	182	8.08	8.20
2.	"	"	"	"	"	167	7.42	
3.	"	"	"	"	"	200	9.20	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ 1:4:8

Date: 12/01/2020

Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M10**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age	Load KN	Compressive Strength- N/mm2	Average
1.	Kavery Layout	5/1/20	12/1/20	22500	7	177	7.86	7.65
2.	"	"	"	"	"	168	7.46	
3.	"	"	"	"	"	172	7.64	

CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ RAFT LAYOUT Date: 30/01/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Raft concrete	23/1/20	30/1/20	22500	07	455	20.22	
2.	Kavery	"	"	"	"	478	21.24	
3.	Layout	"	"	"	"	464	20.62	
4.	"	"	"	"	"	443	19.68	20.03
5.	"	"	"	"	"	461	20.48	
6.	"	"	"	"	"	405	18.00	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ RAFT LAYOUT Date: 30/01/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Raft concrete	23/1/20	30/1/20	22500	07	442	19.64	
2.	Kavery	"	"	"	"	436	19.37	
3.	Layout	"	"	"	"	451	20.04	
4.	"	"	"	"	"	435	19.33	19.28
5.	"	"	"	"	"	411	18.26	
6.	"	"	"	"	"	429	19.06	

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ RAFT LAYOUT Date: 20/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Raft concrete	23/1/20	20/1/20	22500	28	495	22.00	
2.	Kavery	"	"	"	"	501	22.22	
3.	Layout	"	"	"	"	492	21.86	
4.	"	"	"	"	"	510	22.66	22.45
5.	"	"	"	"	"	526	23.37	
6.	"	"	"	"	"	509	22.62	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ RAFT LAYOUT Date: 20/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Raft concrete	23/1/20	20/1/20	22500	28	503	22.35	
2.	Kavery	"	"	"	"	516	22.93	
3.	Layout	"	"	"	"	519	23.06	
4.	"	"	"	"	"	493	21.91	23.01
5.	"	"	"	"	"	546	24.26	
6.	"	"	"	"	"	530	23.55	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ SIDES- LAYOUT Date: 03/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength-N/mm2	Average
1.	Sides concrete	27/1/20	03/2/20	22500	7	440	19.55	19.40
2.	Kavery	"	"	"	"	456	20.26	
3.	Layout	"	"	"	"	434	19.28	
4.	"	"	"	"	"	427	18.97	
5.	"	"	"	"	"	448	19.91	
6.	"	"	"	"	"	415	18.44	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ SIDES- LAYOUT Date: 03/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Sides concrete	27/1/20	03/2/20	22500	7	452	20.08	19.16
2.	Kavery	"	"	"	"	443	19.68	
3.	Layout	"	"	"	"	432	19.20	
4.	"	"	"	"	"	416	18.48	
5.	"	"	"	"	"	435	19.33	
6.	"	"	"	"	"	410	18.22	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ SIDES- LAYOUT Date: 03/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Sides concrete	27/1/20	03/2/20	22500	7	406	18.04	19.11
2.	Kavery	"	"	"	"	425	18.88	
3.	Layout	"	"	"	"	439	19.51	
4.	"	"	"	"	"	440	19.55	
5.	"	"	"	"	"	418	18.57	
6.	"	"	"	"	"	453	20.13	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ SIDES- LAYOUT Date: 03/02/2020

1. **Test report on cement Concrete Cubes:**

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Sides concrete	27/1/20	03/2/20	22500	7	417	18.53	
2.	Kavery	"	"	"	"	432	19.20	
3.	Layout	"	"	"	"	411	18.26	
4.	"	"	"	"	"	432	19.20	18.60
5.	"	"	"	"	"	416	18.48	
6.	"	"	"	"	"	403	17.91	

SHRIYA CONSTRUCTION AND CONSULTANCY

Mob : 99457 44759

Shriya Construction and Consultancy

1133, 3rd Floor, 3rd Stage, B Cross, Yelahanka New Town, Bangalore - 560 064.

NO: YEL/PMC/KAVE/ SIDES- LAYOUT Date: 24/02/2020

1. Test report on cement Concrete Cubes:

Sub: Testing of concrete cubes (for below said no of days – Compressive Strength)

Project: Name of work: "Asphalting to roads at Kaveri layout and surrounding areas in ward no - 03 Yelahanka Satellite Town sub Division".

Ref: Material Testing/PMC/19-20

Report submitted to: Assistant Executive Engineer, Yelahanka Sub Division, BBMP Bangalore.

Name of Agency/ contractor: M/s KRIDL Bangalore.

RESULTS OF COMPRESSIVE STRENGHT OF CONCRETE CUBES

CUBE SPECIMENS

Dimentions of Specimens: 150x150x150mm
Grade Of concrete: **M20**

Table 1.1

SL No	Location	Date of casting	Date of Testing	C/S Area mm2	Age (Days)	Load KN	Compressive Strength- N/mm2	Average
1.	Sides concrete	27/1/20	24/2/20	22500	28	498	22.13	22.38
2.	Kavery	"	"	"	"	509	22.62	
3.	Layout	"	"	"	"	488	21.68	
4.	"	"	"	"	"	502	22.31	
5.	"	"	"	"	"	510	22.66	
6.	"	"	"	"	"	515	22.88	